


## Patent Abstracts of Japan

TITLE : MOLDING METHOD FOR BOTTLE  
WITH GRIP



**CONSTITUTION:** A preform 6 heated to 70-130°C in molds in which a grip 2 having an engaging part 21 is inserted is biaxially orientation blow-molded, a wall of the preform 6 is wound on the part 21 as a bottle with the grip. In this case, temperatures of the bodies 3a, 3b of the molds are set to 80-200°C, and a temperature of a bottom 4 is set to 50-150°C. The bottom 4 having uneven shapes 41, 42, 43 formed substantially linearly symmetrical with directional properties is so set as to be inclined at 20-70 degrees to a vertical plane 22 including a center of the grip and a central axis of the bottle. It is blow-molded in this state, brought into contact with the molds for several seconds to be heat treated, then cooled and removed.

COPYRIGHT: (C)1995,JPO